

TECHINCAL DATA SHEET

HIGH DENSITY POLYETHYLENE

SIRENE HD E 80 PLUS



POLYETHYLENE FOR EXTRUSION AND BLOW MOULDING

PRODUCT DESCRIPTION

Sirene HD E 80 PLUS is high density grade polyethylene in pellet form
It has good properties and it can be used in extrusion and blow moulding application

COLOR

The product is available in black color

PROPERTIES

easy processability
excellent rigidity
good homogeneity
good filtration

APPLICATIONS

Double wall pipe, bottles, plates, nets or others

ADDITIVES

Antioxidant, UV stabilizer can be added under specific request

TYPICAL PROPERTIES

PHYSICAL	VALUE	U.M.	TEST METHOD
MELT FLOW INDEX (190°/5KG)	1,3-2,0	g/10'	ISO 1133:2005
MELT FLOW INDEX (190°/2,16KG)	0,3-0,5	g/10'	ISO 1133:2005
DENSITY	0,945-0,960	g/cm3	ISO 1183

MECHANICAL

FLUXURAL MODULUS (23°)	800	Mpa	ISO 178
TENSILE MODULUS (23°)	780	Mpa	ISO 527-1, -2
TENSILE STRENGHT (23°)	23	Mpa	ISO 527-1, -2

PROCESSING PARAMETERS

MELT TEMPERATURE	180-210	°C	
------------------	---------	----	--

*Reported values has been obtained after several test in prodution
Specific value of the lots can be only issued through our certificates of Analysis under request.*

NOTES

These are typical property not to be considered as specification limits. In order to obtain optimum product properties and suitability users should determine the condition necessary for the intended application.

FURTHER INFORMATIONS**Health and safety**

Resins in our product reach the highest quality standards, but under certain environment some precautions should be considered. Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may degrade if exposed to air during any of the processing and off line-operation. The product of degradation may have therefore unpleasant odour. In higher concentrations, they may cause irritation of mucus membranes. Fabrication areas should be ventilated to carry wat fumes or vapours. Please follow your legislation on the control of emission and pollution prevention.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. While burning, the resin contributes high heat and may generate a dense black smoke.

For further information about safety in handling and processing please refer to the Safety Data Sheet.

Storage:

Resins are packed in 25kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i.e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavourable storage conditions may also intensify the resin's slight characteristic odour.

Resin should be protected from direct sunlight, temperature above 40° and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and applications, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the materiel on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Company information

For further information regarding the SIRE Company visit the web site www.sirespa.com

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specifications, either express or implied, including any warranty of merchantability of fitness for any particular purpose. User shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibition for use specifically noted in this document, SIRE may further prohibit or restrict the sale of its products into certain application.

For Further information please contact a SIRE representative.